

technical data

AXEL

PLASTICS RESEARCH LABORATORIES, INC.
MOLD RELEASES & INTERNAL LUBRICANTS

Mailing Address: Box 77 0855, Woodside, NY 11377
Shipping Address: 58-20 Broadway, Woodside, NY 11377
Tel: 718-672-8300 • Fax: 718-565-7447
E-mail: info@axelplastics.com

MOLD WIZ INT-4E11CC

General: A process aid additive with surfactant properties which is added directly into the aqueous resin solution. The addition of this process aid additive gives the resin improved wetting properties of the paper or substrate being impregnated, reducing or eliminating voids and dry spots. The process aid additive will not interfere with adhesion properties between paper laminates. It will function as an excellent release agent causing the laminate to release easily and cleanly from the caul plate without leaving any residue. **This product contains no silicone, no wax and no metallic stearates.**

Use: Water-based systems
Phenolic Melamine Urea Resins

Composition: Proprietary emulsified product of organic fatty acids, esters and amine with wetting agents and surfactants in a water vehicle.

TYPICAL PROPERTIES:

EFFECTIVE INGREDIENTS:	45 – 50%
SOLIDS:	45 – 50%
COLOR GARDNER:	Light Amber
SPECIFIC GRAVITY:	1.03 @25°C
VISCOSITY:	< 400 cps @25°C
pH:	8.5 – 10.5
FLASH POINT:	Non-Flammable
SHELF LIFE:	Minimum of one year

Application Instructions:

General: For best results, laboratory tests or pre-production trials should determine the optimum addition level. Use 0.25 - 1.0% process aid additive based on solids of additive to solids of resin solution.