

## technical data



PLASTICS RESEARCH LABORATORIES, INC.  
MOLD RELEASES & INTERNAL LUBRICANTS

Mailing Address: Box 77 0855, Woodside, NY 11377  
Shipping Address: 58-20 Broadway, Woodside, NY 11377  
Tel: 718-672-8300 • Fax: 718-565-7447  
E-mail: [info@axelplastics.com](mailto:info@axelplastics.com)

# MOLD WIZ INT-1117LAM

**General:** A non-silicone process aid additive for use in all types of rubber processing which eliminates the need for any external release agent minimizing mold and machine cleaning time. Facilitates processing by increasing the flow characteristics and lubricating qualities of the rubber formulation without affecting its mechanical properties. The cured product can be readily glued, bonded, coated, etc. and there is no exudation or deterioration after prolonged storage. There is an increase in elongation percentage and tensile strength with many formulations.

**Use:** **Silicone Rubber Fluoro-Rubbers**  
**Polyacrylates Hypalon**  
**Chlorosulfonated PE**  
**Epichlorohydrin**  
**High Styrene Rubbers**

**Composition:** Proprietary blend synergistically selected from organic fatty acids, esters, alkanes and alkanols.

### TYPICAL PROPERTIES:

<b>EFFECTIVE INGREDIENTS:</b>	<b>100%</b>
<b>SOLIDS:</b>	<b>100%</b>
<b>COLOR:</b>	<b>Off white</b>
<b>VISCOSITY:</b>	<b>Solid</b>
<b>DROPPING POINT:</b>	<b>235°F / 113°C</b>
<b>FLASH POINT:</b>	<b>Non Flammable</b>
<b>SHELF LIFE:</b>	<b>Minimum of one year</b>

### Application Instructions:

**General:** Beginning with a clean mold will provide accurate results. It is recommended to remove mold release and rubber residue with CLEAN WIZ.

0.2 – 1.0 phr will be effective in most rubber compounds. (2-10 parts 1000 parts rubber). Begin testing with 0.25 and 0.5 phr to determine the optimum level of usage in a particular rubber recipe. Process aid additive may be Banbury mixed or milled in the rubber recipe. If the process aid additive can be milled with the rubber first, it will promote faster mixing of fillers and additives, also reducing tack on the mill. In molding operations, rubber viscosity will be reduced allowing better fill at lower temperature and pressure.

All information given by us about our products is based upon our tests and experience. It is intended for use by persons having technical skill at their own discretion and risk, and we assume no liability in connection with their use.

(071220)