

technical data



Tel: 718-672-8300 • Fax: 718-565-7447
E-mail: info@axelplastics.com

MOLD WIZ INT-1858

General: A process aid additive and mold release with anti-static properties which is incorporated directly into the resin or gel coat eliminating the need for an external mold release agent. An effective addition of process aid additive will not have any adverse effect on the cured resin. The complex polymeric nature of the process aid additive will not interfere with secondary operations such as decorating, silk screen printing, painting, bonding, or plating.

Use: Acrylic Polyester Phenolic
Urethane Modified Polyester

Composition: Proprietary synergistic blend of organic esters and alkoxyated amine combined with wetting agents.

TYPICAL PROPERTIES:

EFFECTIVE INGREDIENTS:	100%
SOLIDS:	100%
COLOR:	Amber to Peach
SPECIFIC GRAVITY:	1.02 @ 25°C
VISCOSITY:	800 - 1400 cps @ 25°C
REFRACTIVE INDEX:	1.461
pH (10% in water):	2.0
FLASH POINT:	365°F / 185°C (C.O.C.)
SHELF LIFE:	Minimum of one year

Application Instructions:

General: For best results, laboratory tests or pre-production trials should determine the optimum addition level. MoldWiz process aid additive are effective within a range of 1 to 10 parts per 1000 resin or rubber by weight, excluding reinforcements, pigments and fillers. High amount of filler may require a higher percentage of additives than the indicated maximum. Always start an evaluation at 5 parts per 1000 (0.5%). Too much additive may retard the cure. Reduce the level of additive or slightly increase the catalyst.

All information given by us about our products is based upon our tests and experience. It is intended for use by persons having technical skill at their own discretion and risk, and we assume no liability in connection with their use.

(081814)