technical data



Tel: 718-672-8300 • Fax: 718-565-7447 E-mail: info@axelplastics.com

MOLD WIZ

INT-33UDK

Powder or Pellet (100% Active)

General: Process aid additive with anti-static properties which is incorporated directly into the resin. Eliminates the need for an external mold release agent. Improves resin flow, improves dispersion of other resin additives (reinforcements, fillers, and pigments), shortens cycle times, reduces temperatures and pressures of molding machines, and reduces or eliminates weld/knit lines. An effective addition of process aid additive will not have any adverse effect on physical properties or secondary operations such as decorating, printing, bonding, or plating.

Use: Polycarbonate-Clear, Polycarbonate Blends, Glass-filled & pigmented grades, High Impact Polystyrene, Acetal

Each component in this formulation has been certified by our raw material suppliers as having direct USFDA approval for food contact.

Composition: Proprietary synergistic blend of organic fatty acids, esters and amides.

TYPICAL PROPERTIES:

EFFECTIVE INGREDIENTS:	100%
SOLIDS:	100%
COLOR:	White
SPECIFIC GRAVITY:	0.830 @ 135°C
DROPPING POINT:	257 – 275°F / 125 – 135 °C
SHELF LIFE:	Minimum of one year
AVAILABILITY:	Powder or Pellet form

Application Instructions:

General: For best results, laboratory tests or pre-production trials should determine the optimum addition level. MoldWiz® process aid additives are effective within a range of 1 to 10 parts per 1000 resin excluding reinforcements, pigments and fillers. A high amount of filler may require a higher percentage of additives than the indicated maximum. Always start an evaluation at 5 parts per 1000 (0.5%). The additive may increase the MFI. Reduce the level of additive or the process temperature to raise the resin viscosity and to eliminate screw slippage.

Mixing: Dry blend the additive by tumbling or use dispenser to meter directly into the resin stream. Additives may be compounded into the resin to make a master-batch.

All information given by us about our products is based upon our tests and experience. It is intended for use by persons having technical skill at their own discretion and risk, and we assume no liability in connection with their use.

(061114)