



PLASTICS RESEARCH LABORATORIES, INC.
MOLD RELEASES & PROCESS ADDITIVES

50 Cambridge Drive, Monroe, CT 06468

Phone: 718-672-8300 • Fax: 718-565-7447
E-mail: info @axelplastics.com

www.axelplastics.com

Technical Data Sheet

MoldWiz®

INT-38HT2
Internal Mold Release
Process Aid Additive

Product Description

A process aid, which is incorporated directly into the resin. Improves resin flow/fill, and improves dispersion of other resin additives (reinforcements, fillers, and pigments). Also shortens cycle times by reducing temperatures and pressures of molding machines, and reduces or eliminates weld/knit lines. An effective addition of process aid additive will not have any adverse effect on physical properties or secondary operations such as decorating, printing, bonding, or plating.

Composition

Proprietary synergistic blend of modified polymers, fatty acids and fatty esters.

Handling

Keep container closed when not in use. Store in dry location below 100°F / 38°C.

Uses

Especially recommended for high-temperature engineering plastics and thermoplastic elastomers (TPU) and their blends/alloys.

Typical Properties

Color	White
Dropping Point	201.2°F / 94.0°C
Shelf Life	1 yr. minimum in original closed container

Instructions for Use

For best results, laboratory tests or pre-production trials should determine the optimum addition level. Mold Wiz® process aid additives are effective within a range of 1 - 20 parts per 1000 resin excluding reinforcements, pigments and fillers. A high amount of filler may require a higher percentage of process aid additive than the indicated maximum. Start an evaluation from 5 parts per 1000 (0.5%).

Mixing: Dry blend the process aid additive by tumbling or use an additive dispenser to meter directly into the resin stream. Process aid additives may be compounded into the resin to make a master-batch. Avoid adding the INT-38HT2 prior to drying the resin. INT-38HT2 should be added after drying.

XTEND, MoldWiz & PasteWiz are registered trademarks of Axel Plastics Research Laboratories.

This information is supplied for technically skilled professionals working at their own risk. AXEL believes the information to be accurate, although the Company assumes no liability in the validity of this information for any specific process or application. Moreover, AXEL will assume no liability from any direct and/or consequential damages of any kind that may arise from the use or non use of AXEL products or information supplied by the Company or its appointed representatives.

05182017