



Technical Data Sheet

50 Cambridge Drive, Monroe CT 06468 USA
+1 203.590.2000 | +1 800.332.AXEL
www.axelplastics.com

RO-59 TM-88

Product Description:

RO-59 TM-88 deposits a thin, dry, bonded PTFE lubricant coating on metallic and non-metallic surfaces. These coatings chemically bond to the substrate either at ambient or slightly elevated temperatures and are functional from well below 32°F to 350°F.

A chemically-bonded TM-88 coating provides better lubricity, durability and wear resistance than TM-8 and TM-4 coatings with no sacrifice in cosmetic appearance.

Use:

Use RO-59 TM-88 as a step-up to RO-59 TM-8 when better lubricity, wearability and good cosmetics are required. Not applicable with food products or pharmaceutical applications.

Composition:

RO-59 products are environmentally safe. They are water based with no VOC's. Also, they are nonflammable, do not affect the ozone layer and do not contribute to the greenhouse effect.

Handling:

Please be sure to read the SDS and follow all precautions including appropriate PPE necessary to handle this product safely. Keep tightly sealed while not in use. Mix well before use, and verify the material is homogenous.

Avoid freezing the product and make sure the material is at ambient temperature prior to use.

Instructions for Use

Dilution:

Dilute 1 gallon of RO-59 concentrate with 3 gallons of reverse osmosis (RO), distilled, or deionized (DI) water. Do not use softened water.

Cleaning:

A clean and dry surface is necessary to ensure proper bonding and functionality of the RO-59 coating. A clean metallic surface and completely free of organic contamination is indicated by complete and uniform wetting of the surface by water with no dry spots and no beading or streaking by the water.

Application:

By dipping, spraying, wipe-on etc. Whatever the method, a sufficient amount of TM-88 should be applied to ensure the complete and uniform wetting of the substrate with no dry spot formation.

TM-88 must be heated to 200°F for 30 minutes to ensure a dry and long lasting coating.

A quick air dry (minutes) after application is necessary to effect proper cosmetic appearance. Proper bonding of the coating is ensured by following the quick air dry with heating at 200°F about 30 minutes in an oven, hot room or infrared.

Cosmetically acceptable coatings are more likely to form by orienting the coated substrate in a vertical position to allow drainage.

A second coating thickness to improve wear resistance and possibly to improve cosmetics is done by application + quick air dry for the first coating followed by reapplication + quick air dry for the second coat + final 200°F heating.

Test the RO-59 coated surface for lubricity by rubbing with a paper towel. A smooth feel indicates the presence of a low friction coating.

FEATURES:

Water-based	No VOC's
Non-flammable	